

ASTM A 416/A 416M Steel Strand, Uncoated Seven-Wire for Prestressed Concrete

ASTM A416 Steel Strand, Uncoated Seven-Wire for Prestressed Concrete

Breaking Strength Requirements

Strand Designation No.	Diameter of Strand, mm [in.]	Minimum Breaking Strength of Strand, kN [lbf]	Steel Area of Strand, mm ² [in. ²]	Weight of Strand kg/1000 m [lb/1000 ft]
Grade 1725 [250]				
6	6.4 [0.250]	40.0 [9 000]	23.2 [0.036]	182 [122]
8	7.9 [0.313]	64.5 [14 500]	37.4 [0.058]	294 [197]
9	9.5 [0.375]	89.0 [20 000]	51.6 [0.080]	405 [272]
11	11.1 [0.438]	120.1 [27 000]	69.7 [0.108]	548 [367]
13	12.7 [0.500]	160.1 [36 000]	92.9 [0.144]	730 [490]
15	15.2 [0.600]	240.2 [54 000]	139.4 [0.216]	1094 [737]
Grade 1860 [270]				
9	9.53 [0.375]	102.3 [23 000]	54.8 [0.085]	432 [290]
11	11.11 [0.438]	137.9 [31 000]	74.2 [0.115]	582 [390]
13	12.70 [0.500]	183.7 [41 300]	98.7 [0.153]	775 [520]
15	15.24 [0.600]	260.7 [58 600]	140.0 [0.217]	1102 [740]

Yield Strength Requirements

Strand Designation No.	Nominal Diameter of Strand, mm [in.]	Initial Load, kN [lbf]	Minimum Load at 1 % Extension, kN [lbf]	
			Low-Relaxation	Normal-Relaxation
Grade 1725 [250]				
6	6.4 [0.250]	4.0 [900]	36.0 [8 100]	34.0 [7 650]
8	7.9 [0.313]	6.5 [1 450]	58.1 [13 050]	54.7 [12 300]
9	9.5 [0.375]	8.9 [2 000]	80.1 [18 000]	75.6 [17 000]
11	11.1 [0.438]	12.0 [2 700]	108.1 [24 300]	102.3 [23 000]
13	12.7 [0.500]	16.0 [3 600]	144.1 [32 400]	136.2 [30 600]
15	15.2 [0.600]	24.0 [5 400]	216.2 [48 600]	204.2 [45 900]
Grade 1860 [270]				
9	9.53 [0.375]	10.2 [2 300]	92.1 [20 700]	87.0 [19 550]
11	11.11 [0.438]	13.8 [3 100]	124.1 [27 900]	117.2 [26 350]
13	12.70 [0.500]	18.4 [4 130]	165.3 [37 170]	156.1 [35 100]
15	15.24 [0.600]	26.1 [5 860]	234.6 [52 740]	221.5 [49 800]